



SAMA di Santon Marinella

Via Volontari della Libertà, 48/c - 30034 Piazza Vecchia di Mira (VE) – ITALY

Tel./Fax +39 041 5676159

e-mail info@samastucchi.it

web site <http://samastucchi.it>

TECHNICAL DATASHEET of the "BACKGROUND for STUCCO CALCE "

- Description: specific background for the Stucco Calce.
- Main Characteristics:
 - high viscosity
 - very easy application and paper sanding

OTHER CHARACTERISTICS

- Ready to use: if needed add just some plain water
- Odorless: it can be applied in any season, even with closed windows.
- Non toxic: acrylic resins are infact totally absent.; in case of contact with the skin rinse with water, don't use synthetic thinners.
- Working temperature: above 10 °C..
- Tools: stainless steel rectangular or triangular trowel.
- Tools Cleaning: plain water.
- Directions for Use: apply one layer of Background for Stucco Calce on walls with cement plaster; gypsum or cardboard (previously removing old paints); wait one/two hours (at 18/20 °C, it depends on temperature and humidity) and apply a second layer if the wall is not smooth enough.
- Hints: apply thin layers.
- Drying: wait one hour at 18 C between layers; wait 2-3 hours for complete drying before using sandpaper. Time intervals change with temperature, humidiy and background characteristics.
- Colour: the Background for Stucco Calce looks nearly white in the original container; once applied and dried up the color shade is white. It is advisable to tint the Background for Stucco Calce in the same shade that is desired for the Stucco Calce finish.
- Yield: 4-5 sqm / kg, if diluted up to 7-8 sqm /kg
- Shelf life: unlimited in a fresh room closed in the original container. When part of the content has been used, the remaining quantity will keep well if carefully closed in the original container.