



**SAMA** di Santon Marinella

Via Volontari della Libertà, 48/c - 30034 Piazza Vecchia di Mira (VE) – ITALY

Tel./Fax +39 041 5676159

e-mail [info@samastucchi.it](mailto:info@samastucchi.it)

web site <http://samastucchi.it>

## TECHNICAL DATASHEET for "STUCCO RELAX"

- Description: natural non-synthetic stucco for interior decoration.
- Main Characteristics:
  - natural: absence of any acrylic or synthetic resin, composition is based on vegetal resins and pure baked quality linseed oils
  - rapid application: up to 15/20 square meters /hour of finished wall

### OTHER CHARACTERISTICS

- Dilution: mix it 1:1 with clean plain water.
- Odorless: the total absence of synthetic resins leaves the stucco odorless, it can be applied in any season, even with closed windows.
- Transpiring: the totally natural composition does not affect the wall transpiration characteristics.
- Non toxic: acrylic resins are infact totally absent; in case of contact with the skin rinse with water, don't use synthetic thinners.
- Fireproof: beeing made with water and vegetal resins our tests confirm that it is fireproof; while the fire-resistance classification has not yet been certified, we estimate that the "Stucco di Antiche Tradizioni" will be certified to comply with class 0 (maximum fire resistance).
- Working temperature: above 5 °C.
- Tools: natural sea-sponge.
- Tools Cleaning: plain water and detergent.
- Directions for Use: apply above the special background for Madreperlato (see specific datasheet). Soak the sponge in the stucco, squeeze it carefully and touch the surface at will. The application can be repeated if a stronger color is desired.
- Drying: 6/8 hours, depending on temperature and humidity.
- Color: all shades available for the Stucco Madreperlato; the final result is always satin. The resulting shade, because of the application technique, will be lighter than the corresponding Madreperlato shade.
- Repeated applications: if the next day after the stucco application you need to correct part of the walls with a stronger color shade, it can be done without re-preparing the wall with sandpaper. The "Stucco Relax" can be re-applied anytime without any problem.



*SAMA di Santon Marinella*

Via Volontari della Libertà, 48/c - 30034 Piazza Vecchia di Mira (VE) – ITALY

Tel./Fax +39 041 5676159

e-mail [info@samastucchi.it](mailto:info@samastucchi.it)

web site <http://samastucchi.it>

- Repairable: in case of damages or wall cracks, the coat of "Stucco Relax" can be repaired.
- Maintenance: for cleaning use only alcohol at 94 C proof or higher.
- Yield: 60/70 sqm with 500 ml of stucco diluted with 500 ml of water.
- Manpower: 15/20 sqm/hour of finished wall.
- Shelf life: unlimited in a fresh room closed in the original container.

**IMPORTANT NOTE**

No special tool or technique is required to remove the "Stucco Relax": 2 coats of standard paint are enough to cover the wall.