



**SAMA** di Santon Marinella

Via Volontari della Libertà, 48/c - 30034 Piazza Vecchia di Mira (VE) – ITALY

Tel./Fax +39 041 5676159

e-mail [info@samastucchi.it](mailto:info@samastucchi.it)

web site <http://samastucchi.it>

## TECHNICAL DATASHEET of the "STUCCO RETE"

- Description: plaster for application of fiberglass net and/or filling of powdery and rough walls.
- Main Characteristics:
  - Background plaster for consolidation of wall surfaces to be treated with decorative stucco

### OTHER CHARACTERISTICS

- Ready to use: if needed just add some plain water
- Working temperature: above 5°C.
- Tools: stainless steel trowel for filling, plastic trowel for net application
- Tools Cleaning: plain water.
- Directions for Use:
  - Net application  
Lay the net flat on the surface and apply the plaster using some pressure; at least two layers of Stucco Rete are needed to "drown" the net completely. Complete smoothing with one coat of "Plaster for Large Surfaces".
  - Filler for powdery and rough walls  
Apply one coat of primer and then proceed as for a net application.
- Drying: wait one hour at 18 C between layers; wait 2-3 hours for complete drying before using sandpaper. Time intervals change with temperature, humidity and background characteristics.
- Yield: 0.66 sqm / kg
- Shelf life: unlimited in a fresh room closed in the original container. If part of the content has been used (but still undiluted), close carefully the container and the remainder will still be usable for long time.

### IMPORTANT

Surfaces treated with our Stucco Rete may be painted after applying one coat of primer.